

TECHNICAL SHEET Nº24.B/e.0804

www.euroguarco.com

Filled PTFE gasket sheet GUAFLON BLUE-SEAL

Gasket sheet composed of PTFE resin reinforced with special glass fibres. The formulation results in a product dimensionally stable under compression load, which does not exhibit the cold flow problems encountered with virgin PTFE, yet retaining its excellent resistance to aggressive chemicals, its "non-sticking" properties, its low electrical conductivity and its ease of cutting. BLUE-SEAL complies with technical delivery conditions for PTFE-based gasket sheets DIN 28091-3 TF-G-O.

Applications:

Designed for use in process piping and equipment in chemical, petrol-chemical, pharmaceutical, pulp & paper and food industry. Suitable for sealing of all chemicals, including strong acids and alkalis, with the exception of molten alkali metals, fluorine gas, hydrogen fluoride and materials that may generate these.

Technical Data (values relate to 2 mm thickness)

Density	ASTM D 792	2.25	g/cm ³
Service limits (recommended)*: Continuous service temperature range Max. Service pressure Chemical application range		-200 ÷ + 280 80 (1120 psig) 0 ÷ 14	°C Bar pH
Compressibility	ASTM F 36	7 ÷ 15	%
Recovery	ASTM F 36	35	%
Creep relaxation (20 MPa, 100°C, 22 hrs)	ASTM F 38	50	%
Tensile Strength	ASTM F 152	17	N/mm ²
Elongation at break	ASTM F 152	300	%
Nitrogen permeability (30 N/mm ² , 40 bar)	DIN 3535/4	0,1	ml/min
Compression Strength σ_{VO} Room Temp. " " σ_{BO} at 100°C : " " σ_{BO} at 200°C :	DIN 28090 "	220 80 50	N/mm ² N/mm ² N/mm ²
Thermal Conductivity	DIN 52612	0.4	W/mK
Costante dielettrica	ASTM D 150	2,1	
Resistività elettrica di volume	ASTM D 257	10^{17}	Ohm/cm
Resistività elettrica di superficie	ASTM D 257	10^{15}	Ohm

^{*} Service limits are indicated for proper assembly conditions and gasket design. Max. Temperature and max. Pressure must not occur simultaneously. M = 2.62 at 1.5 mm -4.6 at 3 mm

Supply data:

Colour: Blue

Standard sheet size: 1,500 x 1,500 mm Tolerance: \pm 20 mm Standard thickness: From 0.5 to 3.0 mm Tolerance: \pm 10%

GUAFLON sheets are available also with insertion of tanged perforated stainless steel sheet.

GUAFLON® jointing manufacture is quality assured in accordance with ISO 9001

Data here reported, corresponding to laboratory and field tests typical results, are meant as non-binding guideline for gasket selection. No guarantee claim can be inferred from these data. When needed, we shall be pleased to assist you with specific technical assistance.

Y = 1937(13.36) at 1.5 mm - 1639(11.3) at 3 mm