



CHEMICAL COMPATIBILITY GUIDE

GoatThroat™ Chemical Compatibility Guide

	GT 100	GT 200	GT 200S	GT 300
A	NITRILE	EPDM	SANTOPRENE	VITON
2,4-D Amine 500	Do Not Use	Good	[n/r]	[n/r]
2,4-D Ester 800	[n/r]	[n/r]	[n/r]	Best
9630 Thinner (Nazdar)	Do Not Use	Caution	Best	Caution
ACB - 30	Best	Best	[n/r]	[n/r]
Acetaldehyde	Do Not Use	Best	[n/r]	Caution
Acetamide	Best	Best	[n/r]	Best
Acetic Acid 10%	Do Not Use	Do Not Use	Do Not Use	Good
Acetic Acid 56%	Do Not Use	Do Not Use	Do Not Use	Good
Acetic Acid up 25 - 85%	Do Not Use	Do Not Use	Do Not Use	Good
Acetic Acid up to 25%	Best	Do Not Use	Do Not Use	Good
acetic acid, 100%,	Do Not Use	Do Not Use	Do Not Use	Do Not Use
Acetic Anhydride	Do Not Use	Caution	Best	Do Not Use
***Acetone	Do Not Use	Caution	Best	Do Not Use
***Acetone, technically pure	Do Not Use	Good	Best	Do Not Use
***Acetone, Traces	Good	Best	Best	Good
Acetonitrile	[n/r]	Best	Best	[n/r]
Acetophenone	Do Not Use	Best	[n/r]	Caution
Acetyl Acetone	Caution	Best	[n/r]	Caution
Acetylene	Best	Caution	caution	Best
Acetylene Tetrabromide	[n/r]	Best	[n/r]	Best
Acrylic Acid	Do Not Use	Best	Do Not Use	Do Not Use
Acrylonitrile (Vinyl Cyanide)	Do Not Use	Best	Best	Do Not Use
Acrylonitrile (Vinyl Cyanide)	Do Not Use	Best	[n/r]	Do Not Use
ACTICIDE 14	[n/r]	[n/r]	[n/r]	Best
ACTICIDE A2	[n/r]	[n/r]	[n/r]	Best
ACTRIL DS	[n/r]	[n/r]	[n/r]	Best
AGRITOX	Best	[n/r]	[n/r]	[n/r]
Aircraft Soap	Best	Best	Best	Best
ALBAROL	[n/r]	[n/r]	[n/r]	Best
Alkazene	Caution	Caution	[n/r]	Good
Allyl Alcohol	Best	Do Not Use	Do Not Use	Caution
Alpha Cypermethrin	[n/r]	[n/r]	[n/r]	Best
Aluminum Acetate	Best	Best	[n/r]	Best
Aluminium Bromide	Best	Best	[n/r]	Best
Aluminium Chloride 20%	Best	Best	Best	Best
Aluminium Fluoride 20%	Best	Best	[n/r]	Best
Aluminium Nitrate	Best	Best	[n/r]	Best
Aluminium Salts	Best	[n/r]	[n/r]	[n/r]
Aluminium Sulfate 10%	Best	Best	Best	Best
Alums- NH3-Cr-K	Best	Best	Best	Caution
Ammonium Carbonate 10%	Best	Best	Best	Best
Ammonium Chloride	Good	Best	Best	Best
Ammonium Dibasic	Best	[n/r]	[n/r]	[n/r]
Ammonium Hydroxide	Good	Best	Best	Good
Ammonium Monobasic	Best	[n/r]	[n/r]	[n/r]
Ammonium Nitrate	Best	Best	Best	Best
Ammonium Persulfate	Do Not Use	Best	[n/r]	Best
Ammonium Phosphate(Di, Tri, & Mono)	Best	Best	Best	Best
Ammonium Salts	Best	[n/r]	[n/r]	[n/r]
Ammonium Sulfate	Best	Best	Best	Best
Ammonium Sulphide	Best	Best	[n/r]	Best
Amyl -Alcohol	Good	Best	Best	Best
Amyl -Chloride	Good	Do Not Use	[n/r]	Good
Amyl Naphthalene	Do Not Use	Caution	[n/r]	Best
Amyl- Acetate	Do Not Use	Good	Best	Do Not Use
Amyl- Borate	Best	Good	[n/r]	Best
Anhydrous Ammonia	[n/r]	Best	[n/r]	[n/r]
Anhydrous Hydrazine	[n/r]	Best	[n/r]	[n/r]
Anhydrous Hydrogen Fluoride	[n/r]	Best	[n/r]	[n/r]
Aniline	Do Not Use	Good	Best	Good
Aniline Dyes	Caution	Caution	[n/r]	Good
Aniline Hydrochloride 20%	Good	Good	[n/r]	Best
Aniline Oil	Do Not Use	Good	[n/r]	Best
Animal Fats	Best	Best	[n/r]	Best
ANSULEX Low pH	Good	Best	Good	Do Not Use
Anti Freeze (glycol)	Good	Best	Good	Do Not Use
Aqua Regia	Do Not Use	Good	[n/r]	Caution
ARMOR ALL PROTECTANT	Do Not Use	Best	Do Not Use	Do Not Use

	GT 100	GT 200	GT 200S	GT 300
A	NITRILE	EPDM	Santoprene	VITON
Arsenic Acid	Best	Best	Best	Best
ART BLASTER (JJ Chem)	Do Not Use	Best	Good	Do Not Use
ASE-60	Best	[n/r]	[n/r]	[n/r]
Automatic Transmission Fluid	Best	Caution	[n/r]	Best
Automotive Brake Fluid	Caution	Best	[n/r]	Caution
B	NITRILE	EPDM	Santoprene	VITON
Baking Soda	Best	Best	Best	Best
BAND-ADE Sawing Fluid	Best	Best	[n/r]	Best
Barium Chloride	Best	Best	[n/r]	Best
Barium Hydroxide	Best	Best	Best	Best
Barium Salts	Best	[n/r]	[n/r]	[n/r]
Barium Sulfide	Good	Best	[n/r]	Best
BARREL	[n/r]	[n/r]	[n/r]	Best
BAYCOR 300	[n/r]	Best	[n/r]	[n/r]
BAYFIDAN 250 EC	[n/r]	Best	[n/r]	[n/r]
BAYLETON 125 EC	[n/r]	[n/r]	[n/r]	Best
BAYTAN C Flowable seed dressing	Best	[n/r]	[n/r]	[n/r]
Beer	Good	Best	Best	Best
Beet Sugar Liquors	Best	Best	[n/r]	Best
Benzaldehyde 10%	Do Not Use	Caution	[n/r]	Caution
Benzene	Do Not Use	Do Not Use	Do Not Use	Good
Benzenesulfonic Acid 10%	Do Not Use	Caution	[n/r]	Best
Benzine (Gasoline)	Do Not Use	Do Not Use	Do Not Use	Best
Benzochloride	[n/r]	Best	[n/r]	[n/r]
Benzoic Acid	Good	Caution	caution	Best
Benzyl Alcohol	Do Not Use	Good	[n/r]	Best
Benzyl Benzoate	Do Not Use	Good	[n/r]	Best
Benzyl Chloride	Do Not Use	Do Not Use	[n/r]	Best
Biodiesel - all types	Do Not Use	Do Not Use	Do Not Use	Best
BIOPREP	Do Not Use	Do Not Use	Do Not Use	Best
Black Sulphate Liquors	Best	Best	[n/r]	Best
BLAZER	Best	[n/r]	[n/r]	[n/r]
BLUE DRESSING	[n/r]	[n/r]	[n/r]	Best
Borax (Sodium Borate)	Good	Best	Best	Best
Bordeaux Mixture (Copper Sulfate Salt)	Best	Best	[n/r]	Best
Boric Acid	Best	Best	Best	Best
Boron Fluids	Best	[n/r]	[n/r]	Best
Brake Fluid (non petroleum)	Do Not Use	Best	[n/r]	Caution
Brine	Best	Best	[n/r]	Best
BRODAL	Best	[n/r]	[n/r]	[n/r]
Bromine	Caution	Good	[n/r]	Best
Bromine- Water	Do Not Use	Do Not Use	[n/r]	Best
Bromobenzene	Do Not Use	Do Not Use	[n/r]	Best
Bromochloro Trifluoroethane	[n/r]	[n/r]	[n/r]	Best
Brunil 850	Do Not Use	Do Not Use	Do Not Use	Best
BRYTOFA	Best	[n/r]	[n/r]	[n/r]
BUCTRIL 200	[n/r]	[n/r]	[n/r]	Best
BUCTRIL MA	[n/r]	[n/r]	[n/r]	Best
BUGMASTER FLO	Best	[n/r]	[n/r]	[n/r]
BULLDOCK 25 EC	[n/r]	[n/r]	[n/r]	Best
BULLDOCK 8 UL	[n/r]	[n/r]	[n/r]	Best
Bunker Oil	Best	Do Not Use	Do Not Use	Best
Butadiene	Good	Do Not Use	Do Not Use	Best
Butane (LPG)	remove	Good	Best	Do Not Use
Butane (LPG)	Best	Do Not Use	Do Not Use	Best
Butanol	Good	Best	Good	Good
Butter	Best	Best	[n/r]	Best
Butyl Acetate	Do Not Use	Best	Best	Do Not Use
Butyl Acetyl Rincinoleate	[n/r]	Caution	[n/r]	Best
Butyl Alcohol	Good	Best	[n/r]	Good
Butyl Amine	Best	Do Not Use	[n/r]	Best
Butyl Carbitol	Best	Best	[n/r]	Best
Butyl Cellosolve	Do Not Use	Best	[n/r]	Do Not Use
Butyl Cellosolve Adipate	Caution	Best	[n/r]	Caution
Butyl Oleate	Good	Caution	[n/r]	Best

GoatThroat™ Chemical Compatibility Guide

	GT 100	GT 200	GT 200S	GT 300
B	NITRILE	EPDM	Santoprene	VITON
Butylene	Best	Do Not Use	Do Not Use	Best
Butyraldehyde	Caution	Caution	[n/r]	Caution
Butyric Acid	Do Not Use	Best	Best	Best
C	NITRILE	EPDM	Santoprene	VITON
Calcine Liquors	Good	Best	[n/r]	[n/r]
Calcium Acetate	Best	Best	Best	Best
Calcium Bisulfide	Best	Do Not Use	[n/r]	Best
Calcium Carbonate (Chalk)	Best	Best	[n/r]	Best
Calcium Chloride (Brine)	Best	Best	Best	Best
Calcium Cyanide	Best	[n/r]	[n/r]	[n/r]
Calcium Hydroxide	Best	Best	Best	Best
Calcium Hypochlorite	Caution	Good	Best	Best
Calcium Nitrate	Best	Best	[n/r]	Best
Calcium Phosphate	Best	[n/r]	[n/r]	[n/r]
Calcium Silicate	Best	[n/r]	[n/r]	[n/r]
Calcium Sulfide	Best	Best	[n/r]	Best
Calcium Sulphite	Best	[n/r]	[n/r]	[n/r]
Calcium Thiosulphate	[n/r]	Best	[n/r]	[n/r]
Calibration Fluid	Do Not Use	Do Not Use	Do Not Use	Best
CALIBRATION FLUID 4113	Best	[n/r]	[n/r]	[n/r]
Cane Sugar Liquors	Best	Best	[n/r]	Best
Caproic Aldehyde	[n/r]	Good	[n/r]	[n/r]
Carbamate	Caution	Caution	[n/r]	Best
Carbitol	Best	Best	[n/r]	Best
Carbolic Acid	Caution	Good	[n/r]	Best
Carbon Bisulfide	Caution	Caution	[n/r]	Best
Carbon Dioxide	Best	Do Not Use	Do Not Use	Best
Carbon Disulphide	Caution	Do Not Use	Do Not Use	Best
Carbon Monoxide	Best	Best	Best	Best
Carbon Tetrachloride	Caution	Do Not Use	Do Not Use	Good
Carbonic Acid	Best	Best	[n/r]	Best
Castor Oil	Best	Best	Good	Best
Catalyst 23Lv	Caution	Best	Best	Good
Caustic Potash	Caution	Best	Do Not Use	Do Not Use
Caustic Potash Lye	Caution	Best	Do Not Use	Do Not Use
Caustic Soda Up to 40%	Caution	Best	Do Not Use	Do Not Use
Caustic Soda up to 60%	Best	Best	Do Not Use	Do Not Use
Cellulosolve	Caution	Good	[n/r]	Caution
Cellulosolve Acetate	Do Not Use	Good	[n/r]	Best
Cellulosolve Butyl	[n/r]	Best	[n/r]	[n/r]
Celluguard	[n/r]	Best	[n/r]	[n/r]
Cetane	Best	[n/r]	[n/r]	[n/r]
China Wood Oil	Best	[n/r]	[n/r]	[n/r]
CHLORDANE	[n/r]	[n/r]	[n/r]	Best
Chloreltol	[n/r]	[n/r]	[n/r]	Best
CHLORFOS	[n/r]	[n/r]	[n/r]	[n/r]
Chlorinated Salt Brine	[n/r]	[n/r]	[n/r]	Best
Chlorinated Solvents	Do Not Use	Do Not Use	[n/r]	Good
Chlorine	Caution	Caution	Caution	Best
Chlorine (Wet)	Caution	Caution	Caution	Best
Chlorine Dioxide	Do Not Use	Caution	[n/r]	Do Not Use
Chloroacetone	Do Not Use	Best	Best	Do Not Use
Chlorobenzene (Mono)	Do Not Use	Do Not Use	Do Not Use	Best
Chlorobromo-Methane	Caution	Good	[n/r]	Do Not Use
Chlorobutadiene	Do Not Use	Do Not Use	[n/r]	Best
Chlorododecane	Do Not Use	Caution	[n/r]	Best
Chloroform	Do Not Use	Do Not Use	Do Not Use	Best
Chlorotoluene	Do Not Use	Caution	[n/r]	Best
Chrome Alum	Best	Best	Best	Best
Chrome Plating Solutions	Best	Caution	[n/r]	Best
Chromic Acid 5%	Do Not Use	Best	[n/r]	Best
Chromic Oxide.88 WT.%,aqueous	Best	[n/r]	[n/r]	[n/r]
CIMPERIAL 1070 (Millicron)	Best	Do Not Use	Do Not Use	Best
CIMSTAR 3890 (Milacron)	Best	Do Not Use	Do Not Use	Best
CIMTECH 95 (Millicron)	Best	Do Not Use	Do Not Use	Best
Citric Acid	Best	Best	Best	Best
Cobalt Chloride	Best	Caution	[n/r]	Best
Coconut Oil	Best	Good	[n/r]	Best
Cod Liver Oil	Best	Best	[n/r]	Best

	GT 100	GT 200	GT 200S	GT 300
C	NITRILE	EPDM	Santoprene	VITON
Coffee	Best	Best	[n/r]	Best
Coliche Liquors	Good	Best	[n/r]	Caution
COOLANOL	Best	[n/r]	[n/r]	[n/r]
Copper Acetate	Good	Best	[n/r]	[n/r]
Copper Chloride	Best	Best	Best	Best
Copper Cyanide	Best	Best	[n/r]	Best
Copper Salts	Best	[n/r]	[n/r]	[n/r]
Copper Sulfate 5% Solution	Best	Best	Best	Best
Corn Oil	Best	Good	[n/r]	Best
CORRECT 100 EC	[n/r]	Best	[n/r]	[n/r]
Cottonseed Oil	Best	Best	Good	Best
Creosote, Coal Tar	Best	Do Not Use	[n/r]	Best
Cresol	Do Not Use	Do Not Use	[n/r]	Best
Cresylic Acid	Do Not Use	Do Not Use	[n/r]	Best
Crude Oil	Good	Do Not Use	[n/r]	Best
Cumene	[n/r]	Do Not Use	[n/r]	Best
Cutting Oil	Best	[n/r]	[n/r]	Best
CX-590CU (Millicron)	Best	Do Not Use	Do Not Use	Best
Cyclohexane	Good	Do Not Use	Do Not Use	Best
Cyclohexanol	Caution	Good	[n/r]	Best
Cyclohexanone	Do Not Use	Caution	Good	Do Not Use
Cyclomethicone	[n/r]	[n/r]	Good	[n/r]
D	NITRILE	EPDM	Santoprene	VITON
D-Limonene	[n/r]	[n/r]	[n/r]	Best
D101	[n/r]	Best	[n/r]	[n/r]
D105	[n/r]	Best	[n/r]	[n/r]
D108	[n/r]	Best	[n/r]	[n/r]
D111	[n/r]	Best	[n/r]	[n/r]
D120	Best	[n/r]	[n/r]	[n/r]
D140	Best	[n/r]	[n/r]	[n/r]
D155	[n/r]	Best	[n/r]	[n/r]
D160	[n/r]	[n/r]	Best	Best
De-icing Fluid	Best	Best	Best	Best
Decalin (Deklin)	Do Not Use	Do Not Use	[n/r]	Best
Decane	Do Not Use	Do Not Use	[n/r]	Best
Demeton-S-Methyl	[n/r]	[n/r]	[n/r]	Best
Denatured Alcohol	Best	Best	[n/r]	Best
Destroyer 115	Do Not Use	Best	Best	Do Not Use
DESTROYER Series (JJ Chem)	Caution	Do Not Use	Do Not Use	Best
DESTROYER SX SERIES	[n/r]	[n/r]	[n/r]	Best
DETER	[n/r]	[n/r]	[n/r]	Best
Detergents	Best	Best	[n/r]	Best
Developing Fluids (photo)	Best	Best	[n/r]	Best
Dextron	Best	[n/r]	[n/r]	[n/r]
Di-ester Synthetic Lubricants	[n/r]	[n/r]	[n/r]	Best
Diacetone	Best	Good	[n/r]	Do Not Use
Diacetone Alcohol	Do Not Use	Best	[n/r]	Do Not Use
DIAZINON 800	[n/r]	[n/r]	[n/r]	Best
Dibenzyl Ether	Do Not Use	Caution	[n/r]	Good
Dibenzyl Sebacate	Caution	Caution	[n/r]	Good
Dibromomethyl Benzene	[n/r]	[n/r]	[n/r]	Best
Diethyl Phthalate	Do Not Use	Best	Best	Good
Diethyl Sebacate	Do Not Use	Good	[n/r]	Caution
Dichloro Butane	[n/r]	[n/r]	[n/r]	Best
Dichloroacetic Acid	Good	Good	Good	Good
Dichlorobenzene	Do Not Use	Do Not Use	[n/r]	Good
Dichloromethane	Caution	Caution	[n/r]	Caution
Diesel Fuel	Do Not Use	Do Not Use	Do Not Use	Best
Diethyl Sebacate	Do Not Use	Caution	caution	Good
Diethylamine	Do Not Use	Best	[n/r]	Do Not Use
Diethylene Glycol	Best	Best	[n/r]	Best
Difluorobromomethane	[n/r]	Good	[n/r]	[n/r]
Disobutyl Ketone	Good	Do Not Use	[n/r]	Do Not Use
Disobutylene	Best	Do Not Use	[n/r]	Best
Disooctyl Sebacate	[n/r]	[n/r]	[n/r]	Good
Diisopropanolamine	[n/r]	Good	[n/r]	[n/r]
Diisopropyl Ketone	Do Not Use	Best	[n/r]	Do Not Use
Diisopropylamine	[n/r]	Best	[n/r]	[n/r]
DIMENSION EC	Do Not Use	Do Not Use	Do Not Use	Best
DIMENSION EW	Do Not Use	Do Not Use	Do Not Use	Best
Dimethicone	[n/r]	Good	Good	[n/r]

GoatThroat™ Chemical Compatibility Guide

	GT 100	GT 200	GT 200S	GT 300
D	NITRILE	EPDM	Santoprene	VITON
Dimethyl Formamide	Do Not Use	Good	Best	Do Not Use
Dimethyl Phthalate	Do Not Use	Good	[n/r]	Good
Dimethylformamide	[n/r]	[n/r]	Best	[n/r]
Dimethylisopropylamine	[n/r]	Best	[n/r]	[n/r]
Diocetyl Phthalate	Good	Best	Good	Best
Diocetyl Sebacate	Do Not Use	Caution	[n/r]	Caution
Dipentene	Good	Caution	[n/r]	Best
Diphenyl	Do Not Use	Do Not Use	[n/r]	Best
Diphenyl Oxide	Do Not Use	Do Not Use	[n/r]	Best
DIPTEREX 500 SL	[n/r]	Best	[n/r]	[n/r]
Distilled Water	Best	Best	Best	Best
DIURON FLOWABLE	Best	[n/r]	[n/r]	[n/r]
DODINE FLOWABLE	Best	[n/r]	[n/r]	[n/r]
DOT Brake Fluid	Best	Best	Best	Best
Dow Corning Silane	Good	Best	Best	Caution
Dry Cleaning Fluid	Best	Good	Best	Good
Dry Cleaning Fluids	Caution	Caution	[n/r]	Best
DTE Light oil	Best	[n/r]	[n/r]	[n/r]
E	NITRILE	EPDM	Santoprene	VITON
EASISOLV 120	Do Not Use	Best	Best	Do Not Use
EASISOLV 701	Do Not Use	Best	Best	Do Not Use
ENDOSULFAN	[n/r]	[n/r]	[n/r]	Best
ENDOSULFAN ULV	[n/r]	[n/r]	[n/r]	Best
Engine Oil	Best	Good	Good	Do Not Use
ENVIRONALL	Caution	Caution	[n/r]	Best
Epoxy Resins	[n/r]	Best	[n/r]	[n/r]
ESI-CRYL 11	Best	[n/r]	[n/r]	[n/r]
Ethane	Best	Do Not Use	[n/r]	Best
Ethanol	Best	Best	Best	Best
Ethanol 95%	Best	Best	Good	Best
Ethanolamine	Best	Best	[n/r]	Do Not Use
ETHREL	Good	[n/r]	[n/r]	[n/r]
Ethyl Acetate	Do Not Use	Good	Best	Do Not Use
Ethyl Acetoacetate	Do Not Use	Best	[n/r]	Do Not Use
Ethyl Acrylate	Do Not Use	Good	[n/r]	Do Not Use
Ethyl Alcohol	[n/r]	Best	Best	Best
Ethyl Benzene	Caution	Do Not Use	Do Not Use	Best
Ethyl Benzoate	Caution	Caution	[n/r]	Best
Ethyl Bromide	[n/r]	[n/r]	[n/r]	Best
Ethyl Cellosolve	Good	Good	[n/r]	Do Not Use
Ethyl Cellulose	Good	Good	[n/r]	Best
Ethyl Chloride	Good	Best	Good	Best
Ethyl Chlorocarbonate	[n/r]	[n/r]	[n/r]	Best
Ethyl Chloroformate	Do Not Use	Good	[n/r]	Do Not Use
Ethyl Cyclopentane	Best	[n/r]	[n/r]	[n/r]
Ethyl ether	Best	[n/r]	[n/r]	[n/r]
Ethyl Formate	Do Not Use	Caution	[n/r]	Best
Ethyl Oxalate	Do Not Use	Best	[n/r]	Do Not Use
Ethyl Pentochlorobenzene	Caution	Caution	[n/r]	Best
Ethyl Silicate	Best	Best	[n/r]	Best
Ethylacrylic Acid	[n/r]	Good	[n/r]	[n/r]
Ethylene Chloride	Do Not Use	Do Not Use	Do Not Use	Best
Ethylene Chlorhydrin	Do Not Use	Best	Best	Do Not Use
Ethylene Diamine	Best	Best	[n/r]	Do Not Use
Ethylene Dibromide	[n/r]	[n/r]	[n/r]	Best
Ethylene Dichloride	Do Not Use	Do Not Use	Do Not Use	Best
Ethylene Glycol	Best	Best	Best	Best
Ethylene Oxide, Liquid	Do Not Use	Best	Best	Best
Ethylmorpholine Stannous	[n/r]	Best	[n/r]	[n/r]
EVERPRO LIQUID (JJ Chem)	Caution	Do Not Use	Do Not Use	Best
F	NITRILE	EPDM	Santoprene	VITON
Fatty Acids	Best	Do Not Use	Do Not Use	Best
Fenamiphos	[n/r]	[n/r]	[n/r]	Best
Ferric Chloride	Best	Best	Best	Best
Ferric Nitrate	Best	Best	[n/r]	Best
FLUOMETURON FLOWABLE	Best	[n/r]	[n/r]	[n/r]
Fluorolube	Good	Best	[n/r]	Good
FOLICUR 250 EC	[n/r]	Best	[n/r]	[n/r]
FOLICUR 250 EW	Best	[n/r]	[n/r]	[n/r]

F, G	GT 100	GT 200	GT 200S	GT 300
FOLICUR 430 SC	Best	[n/r]	[n/r]	Best
FOLIDOL M500	[n/r]	[n/r]	[n/r]	Best
FOLIMAT 800	[n/r]	Best	[n/r]	[n/r]
Formaldehyde	Caution	Caution	Good	Best
Formalin	Caution	Caution	Good	[n/r]
Formic Acid	Do Not Use	[n/r]	Do Not Use	Best
FORMULA 517	Best	[n/r]	[n/r]	[n/r]
FORMULA 520	Best	[n/r]	[n/r]	[n/r]
FORMULA 537	[n/r]	[n/r]	[n/r]	Best
FORMULA 538	Best	[n/r]	[n/r]	[n/r]
FORMULA 540	[n/r]	Best	[n/r]	[n/r]
FORMULA 560	[n/r]	Best	[n/r]	[n/r]
FORMULA 570	[n/r]	Best	[n/r]	[n/r]
FORMULA 575	[n/r]	[n/r]	[n/r]	Best
FREMONT 419	[n/r]	[n/r]	[n/r]	Best
FRESHWATER XT (JJ Chem)	Do Not Use	Best	Good	Do Not Use
FS FORMULA 10184	Good	Best	Best	[n/r]
FS FORMULA 4089	Do Not Use	Good	Good	Do Not Use
FUEL DOCTOR	[n/r]	[n/r]	[n/r]	Best
Fuel Oil	Best	Do Not Use	[n/r]	Best
Fumaric Acid	Good	[n/r]	[n/r]	Best
Furfural	Do Not Use	Best	[n/r]	Good
Furfural Alcohol	Do Not Use	Caution	[n/r]	Best
Furfuraldehyde	[n/r]	Best	[n/r]	[n/r]
Furylcarbinol	[n/r]	Best	[n/r]	[n/r]
Gallic Acid	Best	Best	[n/r]	Best
Gasoline Leaded	Good	Caution	Do Not Use	Best
Gelatin	Best	Best	[n/r]	Best
Glacial Acetic Acid	Do Not Use	Do Not Use	[n/r]	Good
Glaubers Salt	[n/r]	[n/r]	[n/r]	Best
Glucose	Best	Best	Best	Best
Gluearaldehyde	Do Not Use	Best	Do Not Use	Do Not Use
Glycerin	Best	Best	Best	Best
Glycol Ether	[n/r]	[n/r]	[n/r]	Best
Glycols	Best	Best	Best	Best
GREEN SENSE FRAGRANCE	[n/r]	[n/r]	[n/r]	Best
Green Sulfate Liquor	Best	Best	[n/r]	Best
GUSATHION 200 SC	Best	[n/r]	[n/r]	[n/r]
GUSATHION A LIQUID	[n/r]	[n/r]	[n/r]	Best
H	NITRILE	EPDM	Santoprene	VITON
Halothane	[n/r]	[n/r]	[n/r]	Best
Halowax Oil	Caution	Caution	[n/r]	Best
Heavy Water	Best	[n/r]	[n/r]	[n/r]
HELOTHION EC	[n/r]	[n/r]	[n/r]	Best
Hexane	Caution	Do Not Use	Do Not Use	Best
Hexyl Alcohol	Best	Good	[n/r]	Best
HFE Fluids Azeotropes [3M/Novec]	[n/r]	[n/r]	[n/r]	Best
HFE-7000	[n/r]	Best	[n/r]	[n/r]
HFE-7100	[n/r]	Best	[n/r]	[n/r]
HFE-71DA	[n/r]	[n/r]	[n/r]	Best
HFE-71DE	[n/r]	[n/r]	[n/r]	Best
HFE-71IPA	[n/r]	[n/r]	[n/r]	Best
HFE-7200	[n/r]	Best	[n/r]	[n/r]
HFE-72DA	[n/r]	[n/r]	[n/r]	Best
HFE-72DE	[n/r]	[n/r]	[n/r]	Best
HFE-7300	[n/r]	Best	[n/r]	[n/r]
HFE-7500	[n/r]	Best	[n/r]	[n/r]
HFE-7600	[n/r]	Best	[n/r]	[n/r]
HFE-7800	[n/r]	Best	[n/r]	[n/r]
HOME RUN (JJ Chem)	Do Not Use	Best	Good	Do Not Use
Hydraulic Fluid	Best	Good	Good	Do Not Use
Hydraulic Oils (Petroleum)	Best	Do Not Use	[n/r]	Best
Hydrazine	Best	Best	Best	Best
Hydrobromic Acid	Do Not Use	Best	Best	Best
Hydrochloric Acid (25-30%)	Do Not Use	Caution	Caution	Best
Hydrochloric Acid (35%)	Do Not Use	Do Not Use	Caution	Best
Hydrochloric Acid (5-20%)	Caution	Caution	Caution	Best
Hydrochloric Acid 37%	Do Not Use	Do Not Use	Do Not Use	Good
Hydrochloric Acid, 38%	Do Not Use	Do Not Use	Do Not Use	Good

GoatThroat™ Chemical Compatibility Guide

	GT 100	GT 200	GT 200S	GT 300
H	NITRILE	EPDM	Santoprene	VITON
Hydrocyanic Acid	Good	Good	Best	Good
hydrofluoric acid	[n/r]	[n/r]	[n/r]	Best
Hydrofluosilicic Acid	Do Not Use	Do Not Use	[n/r]	Best
Hydrogen Peroxide 35%	Do Not Use	Do Not Use	Do Not Use	Best
Hydrogen Peroxide 90%	Do Not Use	Do Not Use	Do Not Use	Best
Hydrogen Sulfide (Wet) (Cold)	Good	Best	Best	Best
Hydrogen Sulfide (Wet) (Hot)	Caution	Best	[n/r]	Good
Hydroquinone	Best	Best	[n/r]	Best
Hypochlorous Acid 10%	Caution	Good	[n/r]	Good
I	NITRILE	EPDM	Santoprene	VITON
INTRICUT 217	Good	Do Not Use	Do Not Use	Best
Iodine (in Alcohol)	Good	Caution	[n/r]	Best
Isobutyl Alcohol	Good	Best	[n/r]	Best
Isobutyl-n-Butyrate	[n/r]	Best	[n/r]	[n/r]
Isododecane	Best	[n/r]	[n/r]	[n/r]
Isooctane	Best	Do Not Use	Do Not Use	Best
Isopropanol	Best	Best	Best	Best
Isopropyl Acetate	Do Not Use	Good	[n/r]	Do Not Use
Isopropyl Alcohol	Best	Best	Best	Best
Isopropyl Amine	[n/r]	Good	[n/r]	[n/r]
Isopropyl Chloride	Good	Do Not Use	[n/r]	Best
Isopropyl Ether	Best	Caution	Good	Caution
Isopropyl myristate 98%	[n/r]	[n/r]	Good	[n/r]
Isothiazol	Do Not Use	Do Not Use	Do Not Use	Best
J, K, L	NITRILE	EPDM	Santoprene	VITON
J Spray (JJ Chem)	Do Not Use	Best	Good	Do Not Use
J-SPRAY	[n/r]	Best	[n/r]	Best
KELTHANE	[n/r]	[n/r]	[n/r]	Best
Kerosene	Best	Do Not Use	Do Not Use	Best
KILVAL	[n/r]	[n/r]	[n/r]	Best
Kordek 50C	Do Not Use	Do Not Use	Do Not Use	Best
Lactams- Amino Acids	[n/r]	Best	[n/r]	[n/r]
Lactic Acid	Best	Best	Best	Best
Lactones	[n/r]	Good	[n/r]	[n/r]
Lard	Best	Good	[n/r]	Best
LARVIN 375	Best	[n/r]	[n/r]	[n/r]
LARVIN LV	[n/r]	[n/r]	[n/r]	Best
Lavender Oil	Good	Do Not Use	[n/r]	Best
LE - MAT	[n/r]	Best	[n/r]	[n/r]
Lead Acetate	Best	Best	Best	Best
Lead Nitrate	Best	Best	[n/r]	Best
Lead Sulfamate	Good	Best	[n/r]	Best
LEAFEX	Best	[n/r]	[n/r]	Best
LEBAYCID	[n/r]	[n/r]	[n/r]	Best
LEGUMEX	Best	[n/r]	[n/r]	[n/r]
Light Grease	Best	[n/r]	[n/r]	[n/r]
Lime Bleach	Best	Best	[n/r]	Best
Lime Sulphur	Do Not Use	Best	[n/r]	Best
Linoleic Acid	Good	Do Not Use	[n/r]	Best
Linseed Oil	Good	Good	Good	Best
Lubricating Oils (Petroleum)	Best	Do Not Use	Do Not Use	Best
LUV	[n/r]	[n/r]	Best	[n/r]
Lye	Good	Good	[n/r]	Good
M	NITRILE	EPDM	Santoprene	VITON
Macro-Sorb	Do Not Use	Do Not Use	Do Not Use	Best
Magnesium Chloride	Best	Best	Best	Best
Magnesium Hydroxide	Best	Best	Best	Best
Magnesium Salts	Best	Best	Best	Best
Magnesium Sulfate	Best	Best	Best	Best
Magnesium Sulphite	Best	[n/r]	[n/r]	[n/r]
MALATHION	Best	[n/r]	[n/r]	[n/r]
MALDISON 500	[n/r]	[n/r]	[n/r]	Best
Maleic Acid	Good	Best	[n/r]	Best
Maleic Anhydride	Do Not Use	Do Not Use	[n/r]	Best
Malic Acid	Best	Best	[n/r]	Best
MARLIN	[n/r]	[n/r]	[n/r]	Best

	GT 100	GT 200	GT 200S	GT 300
M	NITRILE	EPDM	Santoprene	VITON
MCPA	Best	Best	[n/r]	Best
MCPA 375 SALT	Best	Best	[n/r]	Best
MCPA LVE 500	Best	Best	[n/r]	Best
Mercuric Chloride (Dilute Solu)	Do Not Use	Good	[n/r]	Do Not Use
Mesityl Oxide	[n/r]	[n/r]	[n/r]	Best
METASYSTOX	Do Not Use	Good	[n/r]	Best
Methacrylic Acid	[n/r]	Caution	[n/r]	Good
Methylated Spirits	[n/r]	Best	[n/r]	[n/r]
Methamidos	[n/r]	Best	[n/r]	[n/r]
Methane	Best	Best	[n/r]	Best
Methanol	Do Not Use	Good	Good	Good
Methyl Acetate	Do Not Use	Good	[n/r]	Do Not Use
Methyl Acrylate	Do Not Use	Good	[n/r]	Do Not Use
Methyl Alcohol	Good	Best	Best	Good
Methyl Bromide	Do Not Use	Good	Good	Best
Methyl Butyl Ketone	Do Not Use	Best	Best	Do Not Use
Methyl Cellosolve	Good	Do Not Use	[n/r]	Good
Methyl Cellulose	Do Not Use	Good	[n/r]	Do Not Use
Methyl Chloride	Do Not Use	Good	Do Not Use	Do Not Use
Methyl Chloroformate	[n/r]	[n/r]	[n/r]	Best
Methyl Cyanide	[n/r]	Best	[n/r]	[n/r]
Methyl D-Bromide	[n/r]	[n/r]	[n/r]	Best
Methyl Dichloride	Do Not Use	Do Not Use	[n/r]	Good
Methyl Ether	Good	Do Not Use	[n/r]	Do Not Use
Methyl Ethyl Ketone (MEK)	Do Not Use	Good	Good	Do Not Use
Methyl Isopropyl Ketone	Do Not Use	Do Not Use	[n/r]	Do Not Use
Methyl Mercaptan	[n/r]	Best	[n/r]	[n/r]
Methyl Oleate	Do Not Use	Caution	[n/r]	Best
Methyl Salicylate	Caution	Caution	Best	Good
Methylacrylic Acid	[n/r]	Good	[n/r]	Good
Methylcyclopentane	Do Not Use	Do Not Use	[n/r]	Best
Methylene Chloride	Do Not Use	Do Not Use	Do Not Use	Best
Mild R362	Best	Do Not Use	Do Not Use	Good
Milk	Best	Best	Best	Best
Millenium Clean	Do Not Use	Do Not Use	Best	Do Not Use
Mineral Oil	Best	Do Not Use	Do Not Use	Best
Momentum	Do Not Use	Do Not Use	Do Not Use	Best
Monobromobenzene	[n/r]	[n/r]	[n/r]	Best
Monochlorobenzene	Do Not Use	Do Not Use	[n/r]	Best
Monoethanolamine	Best	Best	[n/r]	Do Not Use
Monothylene	[n/r]	Best	[n/r]	[n/r]
Monomethyl Aniline	Do Not Use	Do Not Use	[n/r]	Best
Monovinyl Acetylene	Best	Best	[n/r]	Best
MRW-2560D	Best	Do Not Use	Do Not Use	Good
N	NITRILE	EPDM	Santoprene	VITON
N-Butyl Acetate	[n/r]	Good	[n/r]	[n/r]
N-Butyl Benzoate	[n/r]	Best	[n/r]	[n/r]
N-Butyl Butyrate	[n/r]	Best	[n/r]	[n/r]
N-Methyl-2pyrrolidone	Do Not Use	Best	Best	Do Not Use
N-Octane	Best	Caution	[n/r]	Best
N-Pentane	Best	[n/r]	[n/r]	Best
N-Propyl Acetone	[n/r]	Best	[n/r]	[n/r]
Naphtha	Caution	Do Not Use	Do Not Use	Best
Naphthalene	Do Not Use	Do Not Use	Do Not Use	Best
Naphthenic Acid	Good	Do Not Use	[n/r]	Best
NAXCAT MOD ACID	[n/r]	[n/r]	[n/r]	Best
Neatsfoot Oil	Best	Caution	[n/r]	Best
NEMACUR 400 EC	[n/r]	[n/r]	[n/r]	Best
Neon	Best	[n/r]	[n/r]	[n/r]
NEVADA ALL PURPOSE CI/DEGREASER	Best	[n/r]	[n/r]	[n/r]
NEVADA BLUE DRESSING	[n/r]	[n/r]	[n/r]	Best
NEVADA PINK SOAP	[n/r]	[n/r]	[n/r]	Best
NEVADA RED DEGREASER	[n/r]	Best	[n/r]	[n/r]
NEVADA YELLOW DEGREASER	[n/r]	Best	[n/r]	[n/r]
Neville Acid	Caution	Caution	[n/r]	Best
Nickel Acetate	Best	Best	[n/r]	Caution
Nickel Chloride	Best	Best	[n/r]	Best
Nickel Sulfate	Best	Best	Best	Best

GoatThroat™ Chemical Compatibility Guide

	GT 100	GT 200	GT 200S	GT 300
N	NITRILE	EPDM	SANTOPRENE	VITON
NITOFOIL	[n/r]	Best	[n/r]	[n/r]
Nitric Acid 5-10% Solution	Do Not Use	Do Not Use	Do Not Use	Best
Nitric Acid 20-50% Solution	Do Not Use	Do Not Use	Do Not Use	Best
Nitric Acid 60-70% Solution	Do Not Use	Do Not Use	Do Not Use	Best
Nitric Acid 70%+ Solution	Do Not Use	Do Not Use	Do Not Use	Fair
Nitrobenzene	Do Not Use	Good	Good	Best
Nitromethane	Do Not Use	Good	[n/r]	Do Not Use
No-Mow	Do Not Use	Do Not Use	Do Not Use	Best
Novec HFE 71DA	Do Not Use	Do Not Use	Do Not Use	Best
Novec HFE 71DE	Do Not Use	Do Not Use	Do Not Use	Best
Novec HFE 72DE	Do Not Use	Do Not Use	Do Not Use	Best
Novec HFE 7600	[n/r]	Best	[n/r]	[n/r]
Novec HFE 7800	[n/r]	Best	[n/r]	[n/r]
Novec HFE-7000	[n/r]	Best	[n/r]	[n/r]
Novec HFE-7100	[n/r]	Best	[n/r]	[n/r]
Novec HFE-71DA	[n/r]	[n/r]	[n/r]	Best
Novec HFE-71DE	[n/r]	[n/r]	[n/r]	Best
Novec HFE-7200	[n/r]	Best	[n/r]	[n/r]
Novec HFE-72DA	[n/r]	[n/r]	[n/r]	Best
Novec HFE-7300	[n/r]	Best	[n/r]	[n/r]
Novec HFE-7500	[n/r]	Best	[n/r]	[n/r]
O	NITRILE	EPDM	Santoprene	VITON
O-Chlorophenol	[n/r]	[n/r]	[n/r]	Best
O-Dichlorobenzene	Best	Caution	[n/r]	Best
Octachlorotoluene	Caution	Caution	[n/r]	Best
Octadecane	Best	Caution	[n/r]	Best
Octagon PD 680	Best	Do Not Use	Do Not Use	Best
Octyl-Alcohol	Best	[n/r]	[n/r]	[n/r]
OFTANOL TURF	[n/r]	[n/r]	[n/r]	Best
Oleic Acid	Do Not Use	Do Not Use	Do Not Use	Best
Olive Oil	Best	Good	[n/r]	Best
OMALA OIL 220	Best	[n/r]	[n/r]	[n/r]
Orthochloro Ethyl Benzene	[n/r]	[n/r]	[n/r]	Best
Oxalic Acid (Cold)	Best	Best	Best	Best
OXAMIN LO	Best	[n/r]	[n/r]	[n/r]
P	NITRILE	EPDM	Santoprene	VITON
P-Cymene	[n/r]	[n/r]	[n/r]	Best
P-Dichlorobenzene	[n/r]	[n/r]	[n/r]	Best
P-Tertiary Butyl Catechol	[n/r]	Best	[n/r]	[n/r]
Palmitic Acid	Best	Good	Best	Best
PANOCTINE	Best	[n/r]	[n/r]	[n/r]
Pantendiol	Do Not Use	Best	Do Not Use	Do Not Use
Paraffin Oil	Best	[n/r]	[n/r]	Best
Parathion Ethyl Methyl	[n/r]	[n/r]	[n/r]	Best
Peanut Oil	Best	Do Not Use	[n/r]	Best
Penair Mil-C-85590	Do Not Use	Do Not Use	Do Not Use	Best
Pentane 2 Methyl	Best	[n/r]	[n/r]	[n/r]
Pentane 2-4 Dimethyl	Best	[n/r]	[n/r]	[n/r]
Penthane 3 Methyl	Best	[n/r]	[n/r]	[n/r]
Perchloric Acid 72%	Do Not Use	Good	Do Not Use	Best
Perchloroethylene	Do Not Use	Do Not Use	Do Not Use	Best
Petroleum	Best	Best	Do Not Use	Best
Phenol (Carbolic Acid)	Caution	Do Not Use	Do Not Use	Best
Phenyl Hydrazine	Do Not Use	Good	[n/r]	Do Not Use
Phenylbenzene	Do Not Use	Caution	[n/r]	Best
Phorone	Caution	Caution	[n/r]	Best
Phosphoric Acid (to 40% Solution)	Do Not Use	Good	Best	Best
Phosphoric Acid 40-100% Solution	Do Not Use	Good	Caution	Best
Phosphoric Acid Crude	Caution	Good	[n/r]	Best
Phosphoric Acid-20%	Caution	Good	Best	Best
Phosphoric Acid-45%	Best	Best	Best	Best
Phosphorous Trichloride Acid	Caution	Best	Best	Best
Pickling Solution	[n/r]	Do Not Use	Caution	Good
Picric Acid	Do Not Use	Good	[n/r]	Best
Pine Oil	Best	[n/r]	[n/r]	[n/r]
Pinene	Do Not Use	Good	[n/r]	Best
Plating Solutions: Antimony	Best	[n/r]	[n/r]	Best
Plating Solutions: Arsenic	Best	[n/r]	[n/r]	Best
Plating Solutions: Brass	Best	[n/r]	[n/r]	Best
Plating Solutions: Bronze	Best	[n/r]	[n/r]	Best

P	GT 100	GT 200	GT 200S	GT 300
	NITRILE	EPDM	SANTOPRENE	VITON
Plating Solutions: Cadmium	Best	[n/r]	[n/r]	Best
Plating Solutions: Chrome	Caution	Best	[n/r]	Best
Plating Solutions: Copper	Best	[n/r]	[n/r]	Best
Plating Solutions: Gold	Best	[n/r]	[n/r]	Best
Plating Solutions: Indium	Best	[n/r]	[n/r]	Best
Plating Solutions: Iron	Best	[n/r]	[n/r]	Best
Plating Solutions: Lead	Best	[n/r]	[n/r]	Best
Plating Solutions: Nickel	Best	[n/r]	[n/r]	Best
Plating Solutions: Silver	Best	[n/r]	[n/r]	Best
Plating Solutions: Tin	Best	[n/r]	[n/r]	Best
Plating Solutions: Zinc	Best	[n/r]	[n/r]	Best
PNB	Good	Best	Do Not Use	Good
Polyvinyl Acetate Emulsion	Best	Best	[n/r]	Best
Potassium Acetate	Best	Best	[n/r]	Best
Potassium Bromate	Best	[n/r]	Best	Best
Potassium Bromide	Best	[n/r]	Best	Best
Potassium Chloride	Best	Best	[n/r]	Best
Potassium Cupro Cyanide	Best	Best	[n/r]	Best
Potassium Cyanide Solutions	Best	Best	Best	Best
Potassium Dichromate	Best	Best	Best	Best
Potassium Hydroxide	[n/r]	Best	[n/r]	[n/r]
Potassium Hydroxide 60%	Do Not Use	Best	Best	Do Not Use
Potassium Nitrate	Best	Best	[n/r]	Best
Potassium Salts	Best	[n/r]	[n/r]	[n/r]
Potassium Sulfate	Best	Best	Best	Best
Precision Press#2	Good	Do Not Use	[n/r]	Best
PREP 720	Good	[n/r]	[n/r]	[n/r]
PRESS WASH 103 (CMG)	Caution	Do Not Use	Do Not Use	Best
PRIMAL ASE-60	Best	[n/r]	[n/r]	[n/r]
Propane (Liquified) (LPG)	Best	Caution	Do Not Use	Best
Propyl Acetate	Do Not Use	Good	[n/r]	Do Not Use
Propyl Alcohol	Good	Best	[n/r]	Best
Propyl Nitrate	[n/r]	Good	[n/r]	Do Not Use
Propylene	Do Not Use	Do Not Use	[n/r]	Best
Propylene Glycol	Best	Best	Best	Best
Prothiofos	[n/r]	[n/r]	[n/r]	Best
Proxel GL	Do Not Use	Do Not Use	Do Not Use	Best
Pyridine Oil	Do Not Use	Good	[n/r]	Do Not Use
Pyroligneous Acid	Good	Caution	[n/r]	Best
Pyrolubo	[n/r]	[n/r]	[n/r]	Best
Q, R	NITRILE	EPDM	Santoprene	VITON
QUINTOZENE FLOWABLE	Best	[n/r]	[n/r]	[n/r]
Rapeseed Oil	Do Not Use	Best	[n/r]	Best
RAXIL C Flowable seed dressing	Best	[n/r]	[n/r]	Best
ROGOR 400	[n/r]	[n/r]	[n/r]	Best
Roots 1-2-3	Do Not Use	Best	[n/r]	Best
ROUNDUP	[n/r]	[n/r]	[n/r]	Best
ROVRAL AQUAFLO	Best	[n/r]	[n/r]	[n/r]
ROVRAL LIQUID	Best	[n/r]	[n/r]	[n/r]
ROVRAL LIQUID S.D.	Best	[n/r]	[n/r]	[n/r]
S	NITRILE	EPDM	Santoprene	VITON
SAFETY PAL	Do Not Use	Caution	caution	Good
Sal Ammoniac	Best	Best	[n/r]	Best
Salicylic Acid	Best	Best	[n/r]	Best
SANTICIZER	[n/r]	Best	[n/r]	[n/r]
Sea Water	Best	Best	Best	Best
SEMEVIN 500 P	Best	[n/r]	[n/r]	[n/r]
SENCOR 480 SC	Best	[n/r]	[n/r]	[n/r]
Sequestrian 30 A	[n/r]	[n/r]	[n/r]	Best
Silicate Esters	Good	Do Not Use	[n/r]	Best
Silicone Fluid	[n/r]	Good	[n/r]	[n/r]
Silicone Greases	Best	Best	Best	Best
Silicone Oils	Best	Best	Do Not Use	Best
Silver Nitrate	Best	Best	Best	Best
Soap Solutions	Best	Best	Best	Best
Soda Ash (Sodium Carbonate)	Best	Best	[n/r]	Best
Sodium Acetate	Best	Best	[n/r]	Good
Sodium Bicarbonate (Baking Soda)	Best	Best	Best	Best
Sodium Bisulfate	Best	Best	Best	Best

GoatThroat™ Chemical Compatibility Guide

	GT 100	GT 200	GT 200S	GT 300
S	NITRILE	EPDM	SANTOPRENE	VITON
Sodium Bisulfite	Best	Best	Best	Best
Sodium Borate	Best	Best	Best	Best
Sodium Carbonate	Good	Best	Best	Best
Sodium Chloride (Salt)	Best	Best	Best	Best
Sodium Cyanide	Best	Best	[n/r]	Best
Sodium Hydroxide (20% Solution)	Best	Best	Best	Good
Sodium Hydroxide (50% Solution)	Best	Best	Best	Do Not Use
Sodium Hydroxide (80% Solution)	Do Not Use	Best	[n/r]	Do Not Use
Sodium Hypochlorite (to 15%)	Do Not Use	Best	Best	Best
Sodium Hypochlorite (to 5%)	Good	Good	Best	Best
Sodium Lauryl Sulfate (dodecyl sulfate 70%)	[n/r]	[n/r]	Best	[n/r]
Sodium Metaphosphate	Best	Best	[n/r]	Best
Sodium Nitrate	Best	Best	Best	Best
Sodium Perborate	Good	Best	[n/r]	Best
Sodium Peroxide	Best	Best	[n/r]	Best
Sodium Phosphate	Best	Best	Best	Best
Sodium Phosphate, Monobasic	Best	Best	[n/r]	Best
Sodium Phosphate, Tribasic	Best	Best	[n/r]	Best
Sodium Salts	Best	[n/r]	[n/r]	[n/r]
Sodium Silicate	Best	Best	[n/r]	Best
Sodium Sulfide	Best	Best	Best	Best
Sodium Sulphate	Best	Best	Best	Best
Sodium Sulphite	Best	Best	[n/r]	Best
Sodium Thiosulphate (Hypo)	Best	Best	[n/r]	Best
Sodium Xylene Sulphonate	[n/r]	[n/r]	[n/r]	Best
Sorbitan Monolaurate Polyoxethylene	Best	[n/r]	[n/r]	[n/r]
Soybean Oil	Best	Best	Good	Best
SPIN FLOWABLE	Best	[n/r]	[n/r]	[n/r]
STAIN (MH)	Caution	Good	Do Not Use	Best
Stannic Chloride	Best	Best	[n/r]	Best
Stannous Chloride	Best	Good	Best	Best
Stearic Acid	Good	Do Not Use	Best	Best
STEN ERASE	Best	[n/r]	[n/r]	Best
Sucrose Solution	Best	Best	[n/r]	Best
Sulfur Chloride	Caution	Do Not Use	[n/r]	Best
Sulfuric Acid (10-30%)	Good	Good	Good	Best
Sulfuric Acid (35-80%)	Do Not Use	Do Not Use	Do Not Use	Best
Sulfuric Acid (85-90%)	Do Not Use	Do Not Use	Do Not Use	Best
Sulfuric Acid (90%+)	Do Not Use	Do Not Use	Do Not Use	Best
Sulfurous Acid	Caution	Best	[n/r]	Best
Sulphur Hexafluoride	Good	Best	[n/r]	Best
Sulphur Liquors	[n/r]	[n/r]	[n/r]	Best
SUPER BLUE	Do Not Use	Best	Good	Do Not Use
SUPRACIDE	[n/r]	[n/r]	[n/r]	Best
SURF -80	Do Not Use	Best	Do Not Use	Do Not Use
T	NITRILE	EPDM	SANTOPRENE	VITON
Tannic Acid	Best	Good	Best	Best
Tartaric Acid	Best	Best	Best	Best
Tera Bromoethane	Do Not Use	Best	[n/r]	Best
Tergitol	[n/r]	[n/r]	Good	[n/r]
Tergitol (Dow)	[n/r]	[n/r]	[n/r]	Best
TERIC GN9	Best	[n/r]	[n/r]	[n/r]
Terpineol	Good	Caution	[n/r]	Best
Tertiary Butyl Alcohol	Do Not Use	Good	[n/r]	Best
Tetrabutyl Titanate	Good	Good	[n/r]	Best
Tetrachloroethane	Do Not Use	Do Not Use	Do Not Use	Best
Tetrachloroethylene	Do Not Use	Do Not Use	Do Not Use	Best
Tetraethyl Lead	Good	Caution	[n/r]	Best
Tetrahydrofuran	Do Not Use	Do Not Use	Good	Do Not Use
Tetraline	Caution	Do Not Use	[n/r]	Best
Thinner	Caution	Caution	Best	Caution
Titanium Tetrachloride	Caution	Do Not Use	[n/r]	Best
TOKUTHION	[n/r]	[n/r]	[n/r]	Best
Toluene	Do Not Use	Good	Do Not Use	Best

	GT 100	GT 200	GT 200S	GT 300
T	NITRILE	EPDM	SANTOPRENE	VITON
Toluene Diisocyanate	[n/r]	Best	[n/r]	[n/r]
TOP COAT (AU SANCURE)	Caution	Good	Good	Best
TOTRIL	[n/r]	[n/r]	[n/r]	Best
TOUGH 450 EC	[n/r]	Best	[n/r]	[n/r]
Transformer Oil	Best	Do Not Use	[n/r]	Do Not Use
Transmission Fluid Type A	Best	Caution	[n/r]	Best
Tri-isopropanolamine	[n/r]	Good	[n/r]	[n/r]
Triacetin	Good	Best	[n/r]	Good
Triaryl Phosphate	[n/r]	Best	[n/r]	[n/r]
Tributoxy Ethyl Phosphate	Caution	Best	[n/r]	Good
Tributyl Phosphate	Do Not Use	Good	[n/r]	Do Not Use
Tributyl Trichloroacetic Acid	[n/r]	Caution	[n/r]	[n/r]
Trichloroethylene	Do Not Use	Do Not Use	Do Not Use	Best
Tricresylphosphate	Caution	Best	[n/r]	Good
TRIDAN	[n/r]	[n/r]	[n/r]	Best
Triethanol Amine	Caution	Best	Best	Do Not Use
TRIMEC 992	Do Not Use	Do Not Use	Do Not Use	Best
Trinitrotol Toluene	Do Not Use	Do Not Use	[n/r]	Good
Trioctyl Phosphate	Do Not Use	Best	[n/r]	Do Not Use
Tripoly Phosphate	[n/r]	Best	[n/r]	[n/r]
TruBlue Deodorizer	Do Not Use	Best	Best	Best
TRUEX 70 SERIES	[n/r]	[n/r]	[n/r]	Best
TRUEX Series (JJ Chem)	Caution	Do Not Use	Do Not Use	Best
Tung Oil	Best	Do Not Use	Do Not Use	Best
Turbine Oil	Best	Do Not Use	[n/r]	Best
Turbo Oil	Best	[n/r]	[n/r]	[n/r]
Turpentine	Good	Good	[n/r]	Best
TWEEN 20	Best	[n/r]	[n/r]	[n/r]
U,V,W,X,Y,Z	NITRILE	EPDM	Santoprene	VITON
Urea	Best	Best	Best	Best
URINEX (JJ Chem)	Do Not Use	Best	Good	Do Not Use
UV-396 (UV-300)	Do Not Use	Caution	Caution	Best
Vaporene	Do Not Use	Best	Do Not Use	Do Not Use
Varnish	Best	Do Not Use	[n/r]	Best
Vegetable Oils	Best	Best	[n/r]	Best
Vertrel Solvents (Dupont)	[n/r]	Best	[n/r]	[n/r]
Vesene 100 Dow	[n/r]	[n/r]	[n/r]	Best
Vinegar	Caution	Best	Best	Best
W 3635 E	Best	[n/r]	[n/r]	[n/r]
W 3671 B	Best	[n/r]	[n/r]	[n/r]
Water	Best	Best	Best	Best
WD 40	Good	[n/r]	[n/r]	Best
White Oil	Best	Caution	[n/r]	Best
White Pine Oil	Good	Caution	[n/r]	Best
Wine and Whiskey	Best	Best	Best	Best
Wood Oil	Best	Good	[n/r]	Best
X77	Best	[n/r]	[n/r]	[n/r]
Xenon	Best	[n/r]	[n/r]	[n/r]
Xylene	Caution	Do Not Use	Do Not Use	Good
Xylool	Do Not Use	Do Not Use	Do Not Use	Good
Zeolites	Good	Best	[n/r]	Best
ZEP Carb X	Do Not Use	Do Not Use	Do Not Use	Best
Zep L.D. Red (Liquid)	Do Not Use	Do Not Use	Do Not Use	Best
ZEP Lubenze Omni	Do Not Use	Do Not Use	Do Not Use	Best
ZEP PLS Protective Lubricating Spray	Good	[n/r]	[n/r]	Best
ZEP Protect-ALL	Do Not Use	Best	Do Not Use	Do Not Use
Zep True Blitz	Do Not Use	Do Not Use	Do Not Use	Best
Zep- Brakewash	Caution	Do Not Use	Do Not Use	Best
Zinc Acetate	Best	Best	[n/r]	Best
Zinc Chloride	Best	Best	Best	Best
Zinc Salts	Best	[n/r]	Best	[n/r]
Zinc Sulfate	Best	Best	Best	Best